

TDS of AC-318F Single Side Butyl Tape with Non-woven Fabric Backing

ITEM		CONDITION	STANDNRD	RESULT	STANDARD
CONTINUAL FORCE Min (steel ball)		23°C	≥8	13.3	GB/T 4851-98
CLARITY HUMIDITY g/m ² 24H		0.3mpa,24h	≤3	0.6	GB/T 12952-03
LOW TEMPERATURE FLEXIBILITY		— 40°C	NO CRACKLE ON SURFACE	NO CRACKLE ON SURFACE	ASTM C731
APPLICATION TEMPERATURE			— 40 to 90°C		
UV RESISTANCE		U.V LIGHT FOR 2000H	NO CHANGE IN COLOR OR HARDNESS. NO CRACKING, KEEP ADHESION	NO CHANGE IN COLOR OR HARDNESS. NO CRACKING, KEEP ADHESION	ASTM G-53
TAKING- OUT FORCE (N/CM)	GLASS PANEL	23°C 300mm/min	≥10	15.8	ASTMD3330-02
	CEMENT SLAB			17.3	
	Al-CASE			14.8	
	Cu-CASE			14.4	
	STAINLESS STEEL SLAB			16.3	
	PVC SLAB			15.7	

NOTE: THE USE LIFE OF THIS PRODUCT IS MORE THAN 20 YEARS.



Devtec Technological Adhesives Ltd.

P.O.B 1397 Hod Hasharon 45112
 Offices: 19 Alexander Yanai St., Petach Tikva, ISRAEL
 Tel.+972-3-9306694 Fax.+972-3-9043717

www.devtec.co.il sales@devtec.co.il

דבטק דבקים טכנולוגים בע"מ

למכתבים: ת.ד. 1397 הוד השרון 45112
 משרדים: אלכסנדר ינאי 19, פתח תקוה
 טל'. 03-9306694 פקס. 03-9043717